



Nest Rubio's 28 day mordant system

1 five gallon plastic bucket

1 lb wool formed in multiple skeins

alum. potassium aluminum. 10% wog (weight of goods) for wearables

25% wog. for non wearables

add to bucket

dissolve alum in hot water

then nearly fill bucket with cold water

stir.

add labeled (your initials, what fiber, date) wool skeins

stir

label bucket with start date

stir skeins every day for 28 days

after days complete, let skeins drip dry and then punch ONE hole in label

do not rinse until just before dyeing